



## CF coated front

Selbstdurchschreibepapier, vorderseitig gestrichen  
Carbonless paper, coated on the front  
Papier autocopiativo, cara recubierta  
Papier autocopiant, couché au recto

### Technische Daten / Technical Data / Datos Técnicos / Données Techniques

Merkmal Property Propiedad Caractéristique	Prüfnorm Standard Norma Norme	Einheit Unit Unidad Unité	Wert Value Valor Valeur					Toleranz Tolerance Tolerancia Tolérance
			57	80	90	130	173	
<b>CF</b>			<b>57</b>	<b>80</b>	<b>90</b>	<b>130</b>	<b>173</b>	
Flächengewicht Basis weight Gramaje Grammage	ISO 536	g/m <sup>2</sup> gsm	57	80	90	130	173	± 4 %
Dicke Caliper Calibre Epaisseur	ISO 534	µm	70	90	105	140	200	± 5
Glätte Bekk (OS) Smoothness Bekk (TS) Lisura Bekk anverso Lissé Bekk recto	ISO 5627	s	50	40	40	40	40	± 20
Weißer R457 Brightness R457 Blancura R457 Blancheur R457	ISO 2470	%	93	93	95	95	95	± 3 %
Reißlänge längs Breaking length md Longitud de rotura Longueur de rupture SM	ISO 1924-1	m	6.500					± 1.500
Feuchte absolut Absolute humidity Humedad absoluta Humidité absolue		%	5,8					± 0,3

Änderungen vorbehalten / subject to change without notice / sujeto a cambio sin previo aviso / sous réserve de modifications